



PRODUCT DATA SHEET

ARCHITEC 400

25th February 2016

WIDTH	380cm
WEIGHT	400gsm
BREAKING FORCE	1050/N 50mm Warp / 1600/N 50mm Weft
BREAKING EXTENSION	80% Weft / 65% Warp
TEAR RESISTANCE (WING TEAR)	300N Warp / 280N Weft
BURSTING PRESSURE	4200 Mean kpa
BURSTING FORCE (STEEL BALL)	2300 Mean N
FABRICATION METHODS	Hot Air Welding: Sewing
FABRIC CARE	OFPANZ Care Label OF-7

COLOUR	UVR%	MEAN UPF	SHADE FACTOR %
ORANGE	94	24	82
BERRY	95	30	89
LEMON	95	25	76
GRAPE	90	14	82
LIME	94	20	87

NORTH ISLAND: PO Box 97-149, 5 Druces Rd, Manukau City, Auckland, New Zealand
Phone (09) 262 2771, Fax (09) 262 3730 Email: sales@wwiggins.co.nz

SOUTH ISLAND: PO Box 483, 97 Magdala Place, Middleton, Christchurch, New Zealand
Phone (03) 339 4375, Fax (03) 339 7376, Email: chsales@wwiggins.co.nz

IFAI proud member
INDUSTRIAL FABRICS ASSOCIATION INTERNATIONAL
www.ifai.com

